

PVC CONDUIT CEMENT



USAGE:

All classes of PVC solvent weld conduit and fittings.

Recommended for use on:

- Rigid PVC Conduit and Fittings
- ENT Conduit and Fittings
- PVC Duct Pipe and Fittings
- Non-pressure conduit systems
- Schedule 40 and Schedule 80 conduit
- Interference-fit PVC joints
- Electrical raceway systems

CONDUIT SIZE:

Up to 6" (15.24 cm)

TEMPERATURE RANGE Use:

-0°F (-18°C) to 120°F (49°C)

CONSISTENCY/COLOR:

Medium Bodied Clear or Gray Color

SET TIME:

30 seconds

COMPLETE CURE TIME:

24 Hours

SPECIFICATIONS:

Meets ASTM D2564 and

AVAILABLE SIZES:

Gray

Stock#	Size
DUITG16	1 pint (473 ml)
DUITG32	1 quart (.95 L)

Clear

DUITC16	1 pint (473 ml)
DUITC32	1 quart (.95 L)

TALON

ULTRA LOW VOC* MEDIUM BODIED PVC CEMENT

Gray



Clear



- **ULTRA LOW VOC Cement**
- **Fast Set, One-Step Cement**
- **Suitable for All Weather Conditions**
- **Works Well on Wet or Dry Conduit**
- **Great for ENT PVC Conduit and Fittings**

J.C. Whitlam Manufacturing Co.
P.O. Box 380 • Wadsworth, OH 44282
U.S. & Canada

Phone: 800-321-8358
FAX: 800-537-0588

International

Phone: 330-334-2524
FAX: 330-334-3005

www.PVC-CEMENT.com



© 2026 J.C. Whitlam Manufacturing Co.

Distributed By:



*Maximum VOC emissions as applied and tested per SCAQMD Rule 1168, Test Method 316A: less than 425 g/l
**Use without primer when acceptable by local code.

WHITLAM

The Industry Standard for Over 125 Years