

BLACK FLASH FLASHING CEMENT COMPOUND BF-SPEC

PRODUCT DESCRIPTION

PRODUCT

BLACK FLASH Flashing Cement Compound

TYPE

BLACK FLASH Flashing Cement Compound is an all weather compound made of only the highest quality, tough plastic asphalt oils with long-fibre. Non-hardening; stays pliable in any weather. Can be applied to damp surfaces; never pulls away from the joint. Won't crack at any temperature.

RECOMMENDED USES

BLACK FLASH Flashing Cement Compound is used for sealing around flashings and chimneys, repairing leaks in roofs, gutters and old flashings.

COLOR/CONSISTENCY

Black heavy paste

TEMPERATURE APPLICATION USE

30°F (-1°C) to 120°F (48°C)

TEMPERATURE RANGE USE

-70°F (-56°C) to 140°F (60°C)

DRYING TIME

Set time: 1 hour to touch.
Complete cure time is 12 hours.

U.S. FEDERAL SPECIFICATION

Meets SS-C-153

APPLICATION PRECAUTIONS

**WARNING:
COMBUSTIBLE.**

**DO NOT USE NEAR HEAT,
SPARKS OR OPEN FLAME.**

KEEP OUT OF REACH OF CHILDREN.

SEE MATERIAL SAFETY DATA SHEET (MSDS) FOR COMPLETE PRECAUTIONS FOR SAFE HANDLING AND USE.

PACKAGING

U.S. Measure:

<u>Stock Code</u>	<u>Size</u>
Cartridge	
BFC	1/10 gal. (.37 L)
Can	
BF32	1 quart (.95 L)
Can w/ Handle	
BF1	1 gal. (3.785 L)
Pail w/ Handle	
BF5	5 gal. (18.9 L)

WEIGHT PER U.S. GALLON

9.16 lbs. (4.2 kg) ±0.2

SHIPPING WEIGHT PER CASE

<u>Stock#</u>	<u>Case Weight</u>	<u>#/Case</u>
BFC	11 lbs. (5.0 kg)	12/case
BF32	33 lbs. (15.0 kg)	12/case
BF1	40 lbs. (18.1 kg)	4/case
BF5	47 lbs. (21.3 kg)	1/case

DIRECTIONS FOR USE

Apply with putty knife or trowel and work well into holes, cracks and crevices so that all entrapped air is eliminated.

Tools can be easily cleaned with common petroleum solvents.

BF-SPEC

© 2005 J.C. Whitlam Manufacturing Company
This product is manufactured in the U.S.A.

The information contained in this bulletin is correct to the best of our knowledge. The recommendations or suggestions herein are made without guarantee or representation as to result, since the conditions of use are beyond our control. We suggest that you evaluate the recommendations contained in this bulletin. No statement is to be construed as violating any copyright or patent. They are intended only as a source of information.



Division of
J.C. Whitlam Mfg. Company
P.O. Box 380
Wadsworth, Ohio 44282
Phone: 330-334-2524
Fax: 330-334-3005
email: info@jcwhtlam.com
website: www.jcwhtlam.com