

CLEAR PRIMER

PLASTIC PIPE PRIMER

PC-SPEC

PRODUCT DESCRIPTION

PRODUCT

CLEAR PRIMER Plastic Pipe Primer

TYPE

CLEAR PRIMER is a primer for cleaning, deglazing and softening ABS, PVC and CPVC pipe and fittings prior to application of appropriate cement.

RECOMMENDED USES

CLEAR PRIMER is formulated with a blend of powerful solvents which makes it a fast acting primer that removes any glaze often found on plastic pipe and fittings and softens the plastic so that it will accept the appropriate plastic solvent cement much more readily.

COLOR/CONSISTENCY

Clear Liquid

TEMPERATURE RANGE USE

0°F (-18°C) to 100°F (38°C)

FOR USE ON:

PVC, ABS and CPVC pipe and fittings. Up through 16" (40.64 cm) diameter.

U.S. FEDERAL SPECIFICATIONS

CLEAR PRIMER meets ASTM F656.

Carries the National Sanitation Foundation Seal for Potable Water and Drain, Waste and Vent (DWV) systems.



PC-SPEC

© 2006 J.C. Whitlam Manufacturing Company
This product is manufactured in the U.S.A.

APPLICATION PRECAUTIONS

WARNING:
EXTREMELY FLAMMABLE.
HARMFUL OR FATAL IF SWALLOWED.
DO NOT USE NEAR HEAT, SPARKS OR OPEN FLAME.
STORE IN COOL, WELL VENTILATED AREA.

CONTAINS TETRAHYDROFURAN AND METHYL ETHYL KETONE. MAY BE ABSORBED THROUGH THE SKIN. HARMFUL OR FATAL IF SWALLOWED.

USE WITH ADEQUATE VENTILATION. AVOID PROLONGED BREATHING OF VAPORS. AVOID CONTACT WITH EYES OR SKIN. KEEP CONTAINER TIGHTLY CAPPED WHEN NOT IN USE.

SEE MATERIAL SAFETY DATA SHEET (MSDS) FOR COMPLETE PRECAUTIONS FOR SAFE HANDLING AND USE.

KEEP OUT OF REACH OF CHILDREN.

PACKAGING

U.S. Measure:

Stock Code	Size
Dauber Top Can	
PC4	¼ pint (118 ml)
PC8	½ pint (237 ml)
PC16	1 pint (473 ml)
PC32	1 quart (.95 L)
1 Gallon Can w/Handle	
PC1	1 gal. (3.785 L)

WEIGHT PER U.S. GALLON

6.6 lbs. (3.0 kg) ±0.2

SHIPPING WEIGHT PER CASE

Stock#	Case Weight	#/Case
PC4	9 lbs. (4.1 kg)	24/case
PC8	15 lbs. (6.8 kg)	24/case
PC16	14 lbs. (6.4 kg)	12/case
PC32	25 lbs. (11.3 kg)	12/case
PC1	50 lbs. (22.7 kg)	6 each

DIRECTIONS FOR USE

1. Check fitting of pipe. If too loose or too tight, pipe should not be used. Ideal fit between pipe and fitting before cleaning and cementing allows pipe to enter to full depth of socket easily.
2. Remove all dust, moisture, grease, oil and any foreign material from pipe and fitting.
3. Apply generous amounts of CLEAR PRIMER to pipe and fitting. If surface is dry when ready to apply cement, apply additional CLEAR PRIMER so that cement is applied to a damp surface.
4. Keep container closed at all times when not using to avoid moisture absorption and vapor losses.
5. Follow all recommended procedures for joining plastic pipe and fittings as stated in ASTM D2855, D2235 and/or F493 where applicable.
6. **DO NOT USE THIS CLEAR PRIMER TO THIN CEMENT.**



Division of
J.C. Whitlam Mfg. Company
P.O. Box 380
Wadsworth, Ohio 44282
Phone: 330-334-2524
Fax: 330-334-3005
email: info@jcwhitlam.com
website: www.jcwhitlam.com