

SELECT-UNYTE

PTFE THREAD SEALING COMPOUND

TF-SPEC

PRODUCT DESCRIPTION

PRODUCT

SELECT-UNYTE PTFE Thread Sealing Compound

TYPE

SELECT-UNYTE is an all purpose, non-seizing, PTFE thread sealing compound that produces a leakproof seal on all types of metal and plastic threaded connections. **SELECT-UNYTE** is a smooth, grit free, completely homogenized, white PTFE paste.

- Non-Separating
- Grit Free
- Non-Toxic
- Easy Cleanup
- Adheres to Oily Threads

RECOMMENDED USES

SELECT-UNYTE will not transfer any taste or odor to the system being sealed. Excellent for food and water systems. **SELECT-UNYTE** will never harden, and is an anti-galling compound making it possible to disassemble pipes and bolts easily after years of service. Suitable for PVC and CPVC threaded connections.

Suitable for use on systems carrying:

Acids, Diluted	Hydraulic Oils
Air, Compressed	Hydrogen
Aliphatic Solvents	Inert Gases
Alkalis, Diluted	Jet Fuel
Ammonia	Kerosene
Brine	Lacquer
Butane	L P Gases
Carbon Dioxide	Mineral Oils
Castor Oils	Naphtha
Chlorinated Water	Natural Gas
Coal Tar Naphtha	Nitrogen Gas
Corrosives	Petroleum Oils
Cutting Oils	Propane
Diesel Fuel Oil	Refrigeration
Fatty Acids	Gases
Freons (All)	Soap, Liquid
Gasohol	Steam Lines
Gasoline	Sugar, Liquid
Glycerin	Vegetable Oils
Glycol	Water
Heating Oils	Xylol
Helium, Gaseous	

TF-SPEC

© 2012 J.C. Whitlam Manufacturing Company
This product is manufactured in the U.S.A.

COLOR/CONSISTENCY

White brushable paste of smooth, grit free consistency. **SELECT-UNYTE** has an indefinite shelf life.

DRYING TIME

The system may be pressurized immediately after assembly. Soft set, non-hardening

TEMPERATURE RANGE USE

Gases:

-50°F (-46°C) to 400°F (204°C)

Liquids:

-50°F (-46°C) to 400°F (204°C)

Brushable to -50°F (-46°C)

PRESSURE RANGE USE

Gases:

up to 3,000 PSI (211 kg/cm²)

Liquids:

up to 10,000 PSI (703 kg/cm²)

FOR USE ON THREADED:

ABS, PVC, CPVC, Delrin*, Zytel*, Fiberglass, Nylon, Polypropylene, Polybutylene, Polyethylene, Celcon**, Cycolac***, and all types of metal.

U.S. FEDERAL SPECIFICATIONS

SELECT-UNYTE exceeds TT-S-1732.

ENVIRONMENTAL STATEMENT

SELECT-UNYTE is formulated with non-toxic inert oils and is free from any lead containing ingredients.

CORROSIVENESS

SELECT-UNYTE is non-corrosive, and prevents the corrosion and seizing of threads.

PACKAGING

U.S. Measure:

Stock Code

Size

Squeeze Tube

TF2 2 ounce (.056 kg)

Brush Top Can

TF4 ¼ pint (118 ml)

TF8 ½ pint (237 ml)

TF8A (display box) ½ pint (237 ml)

TF16 1 pint (473 ml)

TF32 1 quart (.95 L)

1 Gallon Metal Can w/ Handle

TF1 1 gal. (3.785 L)

5 Gallon Plastic Pail w/ Handle

TF5 5 gal. (18.9 L)

55 Gallon Open Head Steel Drum

TF55 55 gal. (208 L)

WEIGHT PER U.S. GALLON

11.9 lbs. (5.4 kg) ± 0.2

SHIPPING WEIGHT PER CASE

Stock#	Case Weight	#/Case
TF2	11 lbs. (5.0 kg)	72/case
TF4	15 lbs. (6.8 kg)	24/case
TF8	23 lbs. (10.4 kg)	24/case
TF8A	13 lbs. (5.9 kg)	12/case
TF16	22 lbs. (10.0 kg)	12/case
TF32	43 lbs. (19.5 kg)	12/case
TF1	52 lbs. (23.6 kg)	4/case
TF5	66 lbs. (29.9 kg)	1 each
TF55	640 lbs. (290.3 kg)	1 each

DIRECTIONS FOR USE

1. Stir well before using.
2. Brush liberally onto male threads.
3. Make up joint in a normal manner.

On large diameter pipe 4" (10.2 cm) and up, first wrap the pipe threads with two or more thicknesses of **Tape-Unyte**® PTFE Tape, then apply **SELECT-UNYTE** over the tape.



Underwriters' Laboratories of Canada Listed for Natural Gas, Gasoline, Petroleum Oils, Propane & Butane

Meets NSF Standard 14 & NSF Standard 61

WHITLAM
PLUMB-PRO
The Industry Standard for Over 100 Years

Division of
J.C. Whitlam Mfg. Company
P.O. Box 380
Wadsworth, Ohio 44282
Phone: 330-334-2524
Fax: 330-334-3005
email: info@jcwhtlam.com
website: www.jcwhtlam.com

*Dupont registered trademarks. **Celanese registered trademark. ***General Electric Plastics registered trademark. PTFE (polytetrafluoroethylene) is the same chemical composition as Dupont Teflon®.

The information contained in this bulletin is correct to the best of our knowledge. The recommendations or suggestions herein are made without guarantee or representation as to result, since the conditions of use are beyond our control. We suggest that you evaluate the recommendations contained in this bulletin. No statement is to be construed as violating any copyright or patent. They are intended only as a source of information.