

# "WEATHERPROOF" ALL WEATHER LOW VOC MEDIUM BODIED PVC CEMENT WET-SPEC

## PRODUCT DESCRIPTION

### PRODUCT

"WEATHERPROOF" All Weather Low VOC Medium Bodied PVC Cement

### TYPE

"WEATHERPROOF" All Weather Low VOC Medium Bodied PVC Cement is a fast setting cement that is formulated for wet or dry conditions and/or conditions where quick pressurization is desired. "WEATHERPROOF" is an all weather cement.

### RECOMMENDED USES

"WEATHERPROOF" is a One-Step Cement for use through 6" (15.24 cm) diameter on all classes of PVC pressure pipe (including Sch. 80) and 8" (20.32 cm) diameter on non-pressure PVC pipe.

### COLOR/CONSISTENCY

Blue Medium Bodied

### TEMPERATURE RANGE USE

0°F (-18°C) to 100°F (38°C)

### PRESSURE RANGE USE

#### Liquids:

Up to 300 PSI (21.1 kg/cm<sup>2</sup>)

### DRYING TIME\*

Partial set time rating:  
Fast - approximately 20 seconds.  
Complete cure time is 24 hours.

### U.S. FEDERAL SPECIFICATIONS

"WEATHERPROOF" All Weather Low VOC Medium Bodied PVC Cement meets ASTM D2564.

Carries the National Sanitation Foundation Seal for Potable Water and Drain, Waste and Vent (DWV) and Sewer Waste (SW) systems.

NSF Standard 14  
NSF Standard 61



### WET-SPEC

© 2009 J.C. Whitlam Manufacturing Company  
This product is manufactured in the U.S.A.

\* NOTE: Both set time and cure time are affected by humidity and temperature and may vary greatly ±.

The information contained in this bulletin is correct to the best of our knowledge. The recommendations or suggestions herein are made without guarantee or representation as to result, since the conditions of use are beyond our control. We suggest that you evaluate the recommendations contained in this bulletin. No statement is to be construed as violating any copyright or patent. They are intended only as a source of information.

## ENVIRONMENTAL STATEMENT

This product emits less than 250 grams per liter VOC when tested according to SCAQMD method 316A.

## APPLICATION PRECAUTIONS

**WARNING:  
EXTREMELY FLAMMABLE.**

**DO NOT USE NEAR HEAT,  
SPARKS OR OPEN FLAME.**

**STORE IN COOL, WELL  
VENTILATED AREA.**

**CONTAINS TETRAHYDROFURAN,  
CYCLOHEXANONE AND METHYL  
ETHYL KETONE. MAY BE ABSORBED  
THROUGH THE SKIN. HARMFUL OR  
FATAL IF SWALLOWED.**

**USE WITH ADEQUATE VENTILATION.  
AVOID PROLONGED BREATHING OF  
VAPORS. AVOID CONTACT WITH  
EYES OR SKIN. KEEP CONTAINER  
TIGHTLY CAPPED WHEN NOT IN USE.**

**KEEP OUT OF REACH OF CHILDREN.**

**SEE MATERIAL SAFETY DATA SHEET  
(MSDS) FOR COMPLETE  
PRECAUTIONS FOR SAFE HANDLING  
AND USE.**

## PACKAGING

### U.S. Measure:

Stock Code	Size
Dauber Top Can	
WET4	¼ pint (118 ml)
WET8	½ pint (237 ml)
WET16	1 pint (473 ml)
WET32	1 quart (.95 L)
1 Gallon Can w/Handle	
WET1	1 gal. (3.785 L)

### WEIGHT PER U.S. GALLON

7.9 lbs. (3.6 kg) ±0.2

## SHIPPING WEIGHT PER CASE

Stock#	Case Weight	#/Case
WET4	10 lbs. (4.5 kg)	24/case
WET8	16 lbs. (7.3 kg)	24/case
WET8A	9 lbs. (4.1 kg)	12/case
(Display Box)		
WET16	15 lbs. (6.8 kg)	12/case
WET32	28 lbs. (12.7 kg)	12/case
WET1	56 lbs. (25.4 kg)	6 each

## DIRECTIONS FOR USE

1. Cut the pipe square and remove all burrs.
2. Check fitting of pipe. If too loose or too tight, pipe should not be used. Ideal fit between pipe and fitting before cementing allows pipe to enter to full depth of socket easily.
3. Remove all dust, moisture, grease, oil and any other foreign material from pipe and fitting. Clean pipe and fitting with WHITLAM LOW VOC PURPLE PRIMER. While surface is still damp with primer, apply cement as follows.
4. Apply enough cement uniformly to pipe and fitting to form a bead of cement at outside end of pipe. Prevent excess cement from forming on bare inside walls of pipe.
5. Brush cement generously on the outside of the pipe to the depth of the fitting. Do not thin cement with primers or cleaners.
6. Immediately after cement is applied, insert pipe to the bottom of the socket, using a quarter twisting motion, and hold in place 30 seconds until cement sets. Assemble parts QUICKLY. If cement is not fluid, re-coat both parts and repeat procedure.
7. Remove excessive cement with a dry cloth only.
8. Allow about 4 minutes for good handling strength. Allow 4 hours for high strength. For best quality joints, remove water or moisture from pipe and fitting and allow 2-24 hours cure time. Cure time before testing depends on size, fit, temperature and pressures. Refer to ASTM Spec. D2564, for recommended set and cure time.
9. Keep container closed at all times when not using to avoid moisture absorption and vapor losses. Keep cement from freezing.
10. Special Blue dye allows you to see application.
11. Follow all recommended procedures for joining PVC pipe and fittings as stated in ASTM Spec. D2564.

 **WHITLAM**  
**PLUMB-PRO**  
The Industry Standard for Over 100 Years

Division of  
J.C. Whitlam Mfg. Company  
P.O. Box 380  
Wadsworth, Ohio 44282  
Phone: 330-334-2524  
Fax: 330-334-3005  
email: info@jcwhitlam.com  
website: www.jcwhitlam.com