

LOW VOC PURPLE PRIMER PLASTIC PIPE PRIMER PPL-SPEC

PRODUCT DESCRIPTION

PRODUCT

LOW VOC PURPLE PRIMER Plastic Pipe Primer

TYPE

LOW VOC PURPLE PRIMER is a primer for cleaning, deglazing and softening ABS, PVC and CPVC pipe and fittings prior to application of appropriate cement.

RECOMMENDED USES

LOW VOC PURPLE PRIMER is formulated with a blend of powerful solvents which makes it a fast acting primer that removes any glaze often found on plastic pipe and fittings and softens the plastic so that it will accept the appropriate plastic solvent cement much more readily. At the same time, it dyes the plastic surface purple to show where the primer has been applied.

COLOR/CONSISTENCY

Purple Liquid

TEMPERATURE RANGE USE

0°F (-18°C) to 100°F (38°C)

FOR USE ON:

PVC, ABS and CPVC pipe and fittings up through 16" (40.64 cm) diameter.

ENVIRONMENTAL STATEMENT

This product emits less than 500 grams per liter VOC when tested according to SCAQMD method 316A.

U.S. FEDERAL SPECIFICATIONS

PURPLE PRIMER meets ASTM F656.

Carries the National Sanitation Foundation Seal for Potable Water and Drain, Waste and Vent (DWV) systems.



PPL-SPEC

© 2020 J.C. Whitlam Manufacturing Company
This product is manufactured in the U.S.A.

APPLICATION PRECAUTIONS

**WARNING:
EXTREMELY FLAMMABLE.
DO NOT USE NEAR HEAT,
SPARKS OR OPEN FLAME.
STORE IN COOL, WELL
VENTILATED AREA.**

CONTAINS TETRAHYDROFURAN, METHYL ETHYL KETONE AND ACETONE. MAY BE ABSORBED THROUGH THE SKIN. HARMFUL OR FATAL IF SWALLOWED.

USE WITH ADEQUATE VENTILATION. AVOID PROLONGED BREATHING OF VAPORS. AVOID CONTACT WITH EYES OR SKIN. KEEP CONTAINER TIGHTLY CAPPED WHEN NOT IN USE.

KEEP OUT OF REACH OF CHILDREN.

SEE SAFETY DATA SHEET (SDS) FOR COMPLETE PRECAUTIONS FOR SAFE HANDLING AND USE.

PACKAGING

U.S. Measure:

<u>Stock Code</u>	<u>Size</u>
Dauber Top Can	
PPL4	¼ pint (118 ml)
PPL8	½ pint (237 ml)
PPL16	1 pint (473 ml)
PPL32	1 quart (.95 L)
1 Gallon Can w/ Handle	
PPL1	1 gal. (3.785 L)

WEIGHT PER U.S. GALLON

6.9 lbs. (3.1 kg) ± 0.2

SHIPPING WEIGHT PER CASE

<u>Stock Code</u>	<u>Case Weight</u>	<u>#/Case</u>
PPL4	8 lbs. (3.6 kg)	24
PPL8	15 lbs. (6.8 kg)	24
PPL16	14 lbs. (6.4 kg)	12
PPL32	26 lbs. (11.8 kg)	12
PPL1	50 lbs. (22.7 kg)	6

DIRECTIONS FOR USE

1. Check fitting of pipe. If too loose or too tight, pipe should not be used. Ideal fit between pipe and fitting before cleaning and cementing allows pipe to enter to full depth of socket easily.
2. Remove all dust, moisture, grease, oil and any foreign material from pipe and fitting.
3. Apply generous amounts of **LOW VOC PURPLE PRIMER** to pipe and fitting. If surface is dry when ready to apply cement, apply additional **LOW VOC PURPLE PRIMER** so that cement is applied to a damp surface.
4. Keep container closed at all times when not using to avoid moisture absorption and vapor losses.
5. Follow all recommended procedures for joining plastic pipe and fittings as stated in ASTM D2855, D2235 and/or F493 where applicable.
6. **DO NOT USE LOW VOC PURPLE PRIMER TO THIN CEMENT.**



The Industry Standard for Over 100 Years

P.O. Box 380 • Wadsworth, OH 44282 U.S.A.
Phone: 1-330-334-2524 • FAX 1-330-334-3005
Email: info@jcwhtlam.com
Website: www.joinpipe.com