

CLEAR CLEANER PLASTIC PIPE CLEANER C-SPEC

PRODUCT DESCRIPTION

PRODUCT

CLEAR CLEANER Plastic Pipe Cleaner

TYPE

CLEAR CLEANER is a cleaner formulated for fast action in preparing plastic by removing any glaze which might be on the surface of the plastic and slightly softens the plastic so that it will readily accept the appropriate primer and solvent weld cement.

RECOMMENDED USES

CLEAR CLEANER is a cleaner for cleaning, deglazing and softening ABS, PVC and CPVC pipe and fittings prior to application of appropriate primer and cement.

COLOR/CONSISTENCY

Clear Liquid

TEMPERATURE RANGE USE

0°F (-18°C) to 100°F (38°C)

DRYING TIME*

Partial set time rating:
Fast - approximately 45 seconds.
Complete cure time is 24 hours.

FOR USE ON THREADED:

ABS, PVC, CPVC pipe and fittings.
Up through 12" (30.48 cm) diameter.

APPLICATION PRECAUTIONS

WARNING:

EXTREMELY FLAMMABLE.

**DO NOT USE NEAR HEAT,
SPARKS OR OPEN FLAME.**

**STORE IN COOL, WELL
VENTILATED AREA.**

**CONTAINS METHYL ETHYL KETONE.
HARMFUL OR FATAL IF SWALLOWED.**

**USE WITH ADEQUATE VENTILATION.
AVOID PROLONGED BREATHING OF
VAPORS. AVOID CONTACT WITH
EYES OR SKIN. KEEP CONTAINER
TIGHTLY CAPPED WHEN NOT IN USE.**

KEEP OUT OF REACH OF CHILDREN.

**SEE SAFETY DATA SHEET (SDS) FOR
COMPLETE PRECAUTIONS FOR SAFE
HANDLING AND USE.**

PACKAGING

U.S. Measure:

<u>Stock Code</u>	<u>Size</u>
Dauber Top Can	
C4	¼ pint (118 ml)
C8	½ pint (237 ml)
C16	1 pint (473 ml)
C32	1 quart (.95 L)
1 Gallon Can w/ Handle	
C1	Gallon (3.785 L)

WEIGHT PER U.S. GALLON

6.75 lbs. (3.1 kg) ± 0.2

SHIPPING WEIGHT PER CASE

<u>Stock Code</u>	<u>Case Weight</u>	<u>#/Case</u>
C4	9 lbs. (4.1 kg)	24
C8	15 lbs. (6.8 kg)	24
C16	14 lbs. (6.4 kg)	12
C32	25 lbs. (11.3 kg)	12
C1	50 lbs. (22.7 kg)	6

DIRECTIONS FOR USE

1. Check fitting of pipe. If too loose or too tight, pipe should not be used. Ideal fit between pipe and fitting before cementing allows pipe to enter to full depth of socket easily.
2. Remove all dust, moisture, grease, oil and any foreign material from pipe and fitting.
3. Apply generous amounts of **CLEAR CLEANER** to pipe and fitting. If surface is dry when ready to apply cement, apply additional **CLEAR CLEANER** so that cement is applied to a damp surface.
4. Keep container closed at all times when not using to avoid moisture absorption and vapor losses.
5. Follow all recommended procedures for joining plastic pipe and fittings as stated in ASTM D2855, D2235, and/or F493 where applicable.
6. **DO NOT USE THIS CLEANER TO THIN CEMENT.**

C-SPEC

© 2022 J.C. Whitlam Manufacturing Company
This product is manufactured in the U.S.A.

The information contained in this bulletin is correct to the best of our knowledge. The recommendations or suggestions herein are made without guarantee or representation as to result, since the conditions of use are beyond our control. We suggest that you evaluate the recommendations contained in this bulletin. No statement is to be construed as violating any copyright or patent. They are intended only as a source of information. *Note: Both set time and cure time are affected by humidity and temperature and may vary greatly ±.



P.O. Box 380 • Wadsworth, OH 44282 U.S.A.
Phone: 1-330-334-2524 • FAX 1-330-334-3005
Email: info@icwhitlam.com
Website: www.joinpipe.com