



# SHARK-BITE



## BITE BACK AT LEAKS WITH SHARK BITE PVC CEMENT

- Ideal for Pool/Spa Installations/Repair
- Fast Set
- One Step Cement\*
- Low V.O.C. Formula
- No Primer Required\*\*
- Works Well on Wet Pipe
- Great for Flexible PVC
- Allows for Immediate Pressure Testing

### SHARK-BITE SPECIFICATIONS

**USAGE:** To solvent weld all classes of PVC pressure and non-pressure solvent weld pipe and fittings.

**AVAILABLE IN:** 4 oz. (118 ml), 16 oz. (473 ml), 32 oz. (.95 L), and 1 Gallon (3.785 L)

**PIPE SIZE:** Up to 6" (15.24 cm) diameter for pressure pipe and 8" (20.32 cm) diameter for non-pressure.

**LIQUID PRESSURE RANGE:** Up to 300 PSI (21 kg/cm<sup>2</sup>)

**CEMENT COLOR:** Aqua Blue which fades to clear when exposed to sunlight.

**TEMPERATURE RANGE:** Best if used at temperatures between 0°F (-17°C) and 120°F (49°C).

**CONSISTENCY:** Medium Bodied

**PARTIAL SET TIME RATING:** Fast - approximately 20 seconds

**COMPLETE CURE TIME:** 24 Hours

**SPECIFICATIONS:** Meets ASTM specification D2564 and ASTM F3328-18

\*Recommended as a One-Step Solvent Weld Cement for Drain, Waste and Vent (DWV) pipe and fittings in non-pressure applications in sizes up to 4" (10.16 cm) where acceptable by local code.

\* Emits less than 425 grams per liter VOC when tested according to SCAQMD method 316A.

\*\* Use without Primer when acceptable by local code



## WHITLAM

[www.joinpipe.com](http://www.joinpipe.com)

J.C. Whitlam Manufacturing Co.  
P.O. Box 380 • Wadsworth, Ohio 44282

U.S. & Canada

Phone: 800-321-8358

Fax: 800-537-0588

International

Phone: +1-330-334-2524

Fax: +1-330-334-3005