HEAT-TYTE FURNACE CEMENT 3000°F (1649°C) TEMPERATURE RATING HT-SPEC

PRODUCT DESCRIPTION

PRODUCT

HEAT-TYTE Furnace Cement

TYPE

Asbestos free, high heat type paste cement for use on metal, wood, stone, brick or masonry. HEAT-TYTE Furnace Cement is grit free paste and contains no sand. HEAT-TYTE Furnace Cement is suitable for use with continuous operating systems with temperatures up to 3000°F (1649°C).

RECOMMENDED USES

HEAT-TYTE Furnace Cement is a premium grade sealant for use in cementing and resetting furnaces, stoves, boilers, and chimney collars. HEAT-TYTE is a practical and permanent paste cement that adheres to metal, wood, stone, masonry or brick. HEAT-TYTE Furnace Cement cures to a fireproof joint which will outlast most furnaces. HEAT-TYTE provides a nonporous, smoke-tight and gas-tight seal.

HEAT-TYTE Furnace Cement also provides excellent bedding for cementing fire brick and for creating special combustion chambers. HEAT-TYTE Furnace Cement can also be used as topping backfill for oil burner chambers. HEAT-TYTE Furnace Cement is suitable for use with continuous operating systems with temperatures up to 3000°F (1649°C).

HEAT-TYTE Furnace Cement has excellent bonding strength and will not sag, run, shrink, pull away, crack or crumble due to heating and cooling of the system. HEAT-TYTE Furnace Cement is solvent resistant.

COLOR/CONSISTENCY

Gray/Paste

HT-SPEC

© 2025 J.C. Whitlam Manufacturing Company This product is manufactured in the U.S.A.

APPLICATION PRECAUTIONS

WARNING: HEAT-TYTE Furnace Cement contains Sodium Silicate. Avoid spattering and contact with skin, eyes, and clothing. It can cause burns to eyes or skin.

DRYING TIME

30 - 20 minutes.

ENVIRONMENTAL STATEMENT

HEAT-TYTE Furnace Cement increases efficiencies of heating equipment and helps save fuel.

HEAT-TYTE Furnace Cement is not formulated with any lead containing ingredients.

The maximum VOC of this product does not exceed 2.83 lbs./gal. (340 g/l).

WEIGHT PER U.S. GALLON

14.8 lbs. (6.7 kg) ± 0.02

PACKAGING

U.S. Measure:

Stock CodeSizePlastic Pail w/HandleHT64½ gallon (1.89 L)HT11 gallon (3.78 L)

SHIPPING WEIGHT PER CASE

Stock

<u>Code</u>	Case Weight	#/Case
HT64	44 lbs. (22.0 kg)	6
HT1	60 lbs. (27.2 kg)	4

DIRECTIONS FOR USE

FOR USE AS A REPAIR SEALANT:

- 1. Remove dust, grease or foreign material by using a damp cloth over parts to be joined. For hard to clean surfaces, use a small amount of mineral spirits. Allow surface to dry thoroughly.
- 2. Apply **HEAT-TYTE Furnace Cement** liberally with a trowel, spatula, or putty knife to repair area.
- 3. Allow each application to dry before successive applications.
- 4. Allow 4-6 hours for **HEAT-TYTE** Furnace Cement to cure before applying heat.

FOR USE AS A GASKET CEMENT:

- 1. Remove dust, grease or foreign material by using a damp cloth over parts to be joined.
- 2. Apply **HEAT-TYTE Furnace Cement** liberally with a trowel or putty knife to the door next to the gasket.
- 3. Press the gasket into place and close the door to ensure a proper fit.
- 4. Clean off excess cement before drying.
- 5. Allow 4-6 hours for **HEAT-TYTE Furnace Cement** to cure before applying heat.

RESTRICTIONS:

Do not apply to wet surfaces. In situations where the combustion chamber has corroded, consult a professional HVAC specialist. Do not attempt to repair.



P.O. Box 380 ● Wadsworth, OH 44282 U.S.A. Phone: 1-330-334-2524 ● FAX 1-330-334-3005 Email: info@jowhitlam.com Website: www.furnacecement.com

The information contained in this bulletin is correct to the best of our knowledge. The recommendations or suggestions herein are made without guarantee or representation as to result, since the conditions of use are beyond our control. We suggest that you evaluate the recommendations contained in this bulletin. No statement is to be construed as violating any copyright or patent. They are intended only as a source of information.