

TYTE-UNYTE® THREAD SEALING COMPOUND T-SPEC

PRODUCT DESCRIPTION

PRODUCT

TYTE-UNYTE® Thread Sealing Compound

“Standard of the Industry Since 1900”

DESCRIPTION

TYTE-UNYTE® is a smooth, grit-free, gray, paste-type thread sealing compound for use on all types of metal threaded connections.

TYTE-UNYTE® is thixotropic; will not drip or separate in the container. It is noncorrosive, nonpoisonous and never hardens.

RECOMMENDED USES

TYTE-UNYTE® will never harden and is an anti-galling compound making it possible to disassemble pipes and bolts easily after years of service.

Suitable for use on systems carrying:

Acids, Dilute
Air, Compressed
Alkalis, Dilute
Ammonia
Brine
Natural Gas
Steam Lines
Sugar, Liquid
Water (Hot or Cold)

COLOR/CONSISTENCY

Gray, brushable, thixotropic, no-drip paste of smooth, grit-free consistency.

TEMPERATURE RANGE USE

Gases:

-15°F (-26°C) to 400°F (204°C)

Liquids:

-15°F (-26°C) to 400°F (204°C)

Brushable to:

-15°F (-26°C)

PRESSURE RANGE USE

Gases:

up to 1,000 PSI (145 kPa)

Liquids:

up to 2,000 PSI (290 kPa)

DRYING TIME*

Soft set, non-hardening state for easy disassembly after years of service.

FOR USE ON THREADED

All types of metal connections.

CORROSIVENESS

T-U TYPE 555 is non-corrosive, and prevents the corrosion of threads.

U.S. FEDERAL SPECIFICATIONS

T-U TYPE 555 exceeds TT-A-580D.

Meets ANSI LC 7-2009 for Pipe Joint Sealing Compounds and Materials

ENVIRONMENTAL STATEMENT

TYTE-UNYTE® is formulated with non-toxic inert oils and carbonates and contains no lead or silicone.

WEIGHT PER U.S. GALLON

14.6 lbs. (6.6 kg) ± 0.2

PACKAGING

U.S. Measure:

Stock Code	Size
Squeeze Tube	
T2	2 oz. (.056 kg)
Brush Top Can	
T8	½ pint (1 lb.) (.454 kg)
T16	1 pint (2 lb.) (.92 kg)
6 Lb. Pail w/ Handle	
T6	6 lbs. (2.72 kg)
5 Gallon Plastic Pail w/ Handle	
T50	50 lbs. (5 gal.) (22.68 kg)
55 Gallon Open Head Steel Drum	
T600	600 lbs. (55 gal.) (208 L)

SHIPPING WEIGHT PER CASE

Stock Code	Case Weight	#/Case
T2	10 lbs. (4.5 kg)	72
T8	26 lbs. (11.8 kg)	24
T16	25 lbs. (11.3 kg)	12
T6	31 lbs. (14.1 kg)	4
T50	54 lbs. (24.5 kg)	1
T600	640 lbs. (290.3 kg)	1

DIRECTIONS FOR USE

1. Stir well before using.
2. Clean oil, dirt, grease, or any foreign materials from threads.
3. Apply only to male thread with a stiff brush.
4. Make up joint in a normal manner.
5. TYTE-UNYTE® will not harden, shrink, crumble or break. Lubricates as it seals.

T-SPEC

© 2025 J.C. Whitlam Manufacturing Company
This product is manufactured in the U.S.A.



P.O. Box 380 • Wadsworth, OH 44282 U.S.A.
Phone: 1-330-334-2524 • FAX 1-330-334-3005
Email: info@jcwhitlam.com
Website: www.joinpipe.com

The information contained in this bulletin is correct to the best of our knowledge. The recommendations or suggestions herein are made without guarantee or representation as to result, since the conditions of use are beyond our control. We suggest that you evaluate the recommendations contained in this bulletin. No statement is to be construed as violating any copyright or patent. They are intended only as a source of information. *Note: Both set time and cure time are affected by humidity and temperature and may vary greatly ±.