

TALON™ ALL PURPOSE CLEAR REGULAR BODIED LOW VOC CEMENT APR-SPEC

PRODUCT DESCRIPTION

PRODUCT

TALON™ All Purpose Clear Regular Bodied Low VOC Cement

TYPE

TALON™ All Purpose Clear Regular Bodied Low VOC Cement is a regular bodied solvent weld cement of smooth consistency for use in solvent welding ABS, PVC or CPVC solvent weld plastic pipe and fittings. It will also solvent weld ABS to PVC or PVC to CPVC or CPVC to ABS provided tolerances of pipe and fittings match. Should be used in conjunction with Whitlam Low VOC Clear Cleaner or Whitlam Low VOC Purple Primer.

RECOMMENDED USES

TALON™ All Purpose Clear Regular Bodied Low VOC Cement is specially formulated to solvent weld through 4" (10.16 cm) diameter Sch. 40 and Sch. 80, ABS, PVC and Sch. 40 CPVC pipe.

COLOR/CONSISTENCY

Clear Regular Bodied

TEMPERATURE RANGE USE

40°F (5°C) to 100°F (38°C)

PRESSURE RANGE USE

Liquids:

Up to 600 PSI (42 kg/cm²) on ABS*

Up to 300 PSI (21 kg/cm²) on PVC*

Up to 200 PSI (14 kg/cm²) on CPVC*

DRYING TIME**

Partial set time rating:

Fast - approximately 45 seconds.

Complete cure time is 24 hours.

APPLICATION PRECAUTIONS

WARNING:

EXTREMELY FLAMMABLE.

**DO NOT USE NEAR HEAT,
SPARKS OR OPEN FLAME.**

**STORE IN COOL, WELL
VENTILATED AREA.**

CONTAINS TETRAHYDROFURAN AND METHYL ETHYL KETONE. MAY BE ABSORBED THROUGH THE SKIN. HARMFUL OR FATAL IF SWALLOWED.

USE WITH ADEQUATE VENTILATION. AVOID PROLONGED BREATHING OF VAPORS. AVOID CONTACT WITH EYES OR SKIN. KEEP CONTAINER TIGHTLY CAPPED WHEN NOT IN USE.

KEEP OUT OF REACH OF CHILDREN.

SEE SAFETY DATA SHEET (SDS) FOR COMPLETE PRECAUTIONS FOR SAFE HANDLING AND USE.

PACKAGING

U.S. Measure:

<u>Stock Code</u>	<u>Size</u>
Dauber Top Can	
APR4	¼ pint (118 ml)
APR8	½ pint (237 ml)
APR16	1 pint (473 ml)
APR32	1 quart (.95 L)
1 Gallon Can w/ Handle	
APR1	1 gallon (3.785 L)

WEIGHT PER U.S. GALLON

7.6 lbs. (3.5 kg) ± 0.2

SHIPPING WEIGHT PER CASE

<u>Stock Code</u>	<u>Case Weight</u>	<u>#/Case</u>
APR4	10 lbs. (4.5 kg)	24
APR8	16 lbs. (7.3 kg)	24
APR16	15 lbs. (6.8 kg)	12
APR32	28 lbs. (12.7 kg)	12
APR1	56 lbs. (25.4 kg)	6

DIRECTIONS FOR USE

1. Cut the pipe square and remove all burrs.

2. Check fitting of pipe. If too loose or too tight, pipe should not be used. Ideal fit between pipe and fitting before cementing allows pipe to enter to full depth of socket easily.

3. Remove all dust, moisture, grease, oil and any other foreign material from pipe and fitting. Clean pipe and fitting with CLEAR CLEANER. While surface is still damp with primer, apply cement as follows.

4. Apply enough cement uniformly to pipe and fitting to form a bead of cement at outside end of pipe. Prevent excess cement from forming on bare inside walls of pipe.

5. Brush cement generously on the outside of the pipe to the depth of the fitting. Do not thin cement with primers or cleaners.

6. Immediately after cement is applied, insert pipe to the bottom of the socket, using a quarter twisting motion, and hold in place 30 seconds until cement sets. Assemble parts QUICKLY. If cement is not fluid, re-coat both parts and repeat procedure.

7. Remove excessive cement with dry cloth only.

8. Allow about 30 minutes for good handling strength. Allow 4 hours for high strength. For best quality joints, remove water or moisture from pipe and fitting and allow 2-24 hours cure time. Cure time before testing depends on size, fit, temperature and pressures. Refer to ASTM Spec. D2855, D2235, and/or F493 where applicable for recommended set and cure time.

9. Keep container closed at all times when not using to avoid moisture absorption and vapor losses. Keep cement from freezing.

10. Follow all recommended procedures for joining PVC pipe and fittings as stated in ASTM Spec. D2855, D2235, and/or F493 where applicable.



WHITLAM
The Industry Standard for Over 100 Years

APR-SPEC

© 2025 J.C. Whitlam Manufacturing Company
This product is manufactured in the U.S.A.

P.O. Box 380 • Wadsworth, OH 44282 U.S.A.
Phone: 1-330-334-2524 • FAX 1-330-334-3005
Email: info@jcwhitlam.com
Website: www.joinpipe.com

The information contained in this bulletin is correct to the best of our knowledge. The recommendations or suggestions herein are made without guarantee or representation as to result, since the conditions of use are beyond our control. We suggest that you evaluate the recommendations contained in this bulletin. No statement is to be construed as violating any copyright or patent. They are intended only as a source of information.

* LIQUID PRESSURE RANGE: For a 2" (5.08 cm) diameter solvent welded pipe and fitting tested under liquid pressure at 73° (23°C). Sizes vary in accordance with pipe manufacturer's specifications for pressure ratings of pipe. ** NOTE: Both set time and cure time are affected by humidity and temperature and may vary greatly ±.